


**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification 5 :</b> <b>A61M 29/02, A61F 2/04</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 93/19804</b> <b>(43) International Publication Date:</b> 14 October 1993 (14.10.93)
<b>(21) International Application Number:</b> PCT/US93/02970 <b>(22) International Filing Date:</b> 30 March 1993 (30.03.93)  <b>(30) Priority data:</b> 07/861,253 31 March 1992 (31.03.92) US 07/910,631 8 July 1992 (08.07.92) US  <b>(71) Applicant:</b> BOSTON SCIENTIFIC CORPORATION [US/US]; 480 Pleasant Street, Watertown, MA 02172 (US).  <b>(72) Inventor:</b> HEATH, Kevin, R. ; 44 Waban Avenue, Providence, RI 02908 (US).  <b>(74) Agent:</b> WILLIAMS, John, N.; Fish & Richardson, 225 Franklin Street, Boston, MA 02110 (US).		<b>(81) Designated States:</b> CA, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> <i>With international search report.</i> <i>With amended claims.</i>
<b>(54) Title:</b> TUBULAR MEDICAL ENDOPROSTHESES    <b>(57) Abstract</b>  A tubular prosthesis device (10) for use within the body. The device (10) includes, a metal filament (11) material formed of metal outer member (4) having an exposed outer surface and a core (8) within the extended outer member formed of a different metal than the outer member. The core (8) is secured within and substantially enclosed by the outer member (10). The device can be reduced to a small size for introduction into the body lumen and expandable to a sufficiently large size to engage the wall of the body lumen. Stents (10) formed of composite wires (11) are shown.		

BEST AVAILABLE COPY

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NL	Netherlands
BE	Belgium	GN	Guinea	NO	Norway
BF	Burkina Faso	GR	Greece	NZ	New Zealand
BG	Bulgaria	HU	Hungary	PL	Poland
BJ	Benin	IE	Ireland	PT	Portugal
BR	Brazil	IT	Italy	RO	Romania
CA	Canada	JP	Japan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SK	Slovak Republic
CI	Côte d'Ivoire	LI	Liechtenstein	SN	Senegal
CM	Cameroon	LK	Sri Lanka	SU	Soviet Union
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	MC	Monaco	TG	Togo
DE	Germany	MG	Madagascar	UA	Ukraine
DK	Denmark	MI	Mali	US	United States of America
ES	Spain	MN	Mongolia	VN	Viet Nam
FI	Finland				

- 1 -

**TUBULAR MEDICAL ENDOPROSTHESES**Field of the Invention

This invention relates to tubular endoprotheses  
5 to be used inside the body.

Background of the Invention

Tubular endoprotheses such as medical stents are placed within the body to perform a function such as maintaining a body lumen open, for example, a passageway  
10 occluded by a tumor or a blood vessel restricted by plaque. Tubular endoprotheses in the form of grafts are used to substitute for or reinforce a lumen, such as the aorta or other blood vessels which have been weakened, e.g., by an aneurysm.

15 Typically, these endoprotheses are delivered inside the body by a catheter that supports the device in a compacted or otherwise reduced-size form as it is transported to the desired site. The size is particularly small when a percutaneous insertion  
20 technique is employed. Upon reaching the site, the endoprosthesis is expanded so that it engages the walls of the lumen.

The expansion mechanism may involve forcing the endoprosthesis to expand radially outwardly, for example,  
25 by inflation of a balloon carried by the catheter, to plastically deform and fix the device at a predetermined expanded position in contact with the lumen wall. The expanding means, the balloon, can then be deflated and the catheter removed.

30 In another technique, the endoprosthesis is formed of a highly elastic material that can be reversibly compacted and expanded. During introduction into the body, the endoprosthesis is restrained in the compacted condition and upon reaching the desired site for  
35 implantation, the restraint is removed, enabling the

- 2 -

device to self-expand by its own internal elastic restoring force.

In many cases, X-ray fluoroscopy is used to view an endoprosthesis within the body cavity to monitor placement and operation. The device may also be viewed by X-ray film after placement for medical follow-up evaluation. To date, the requirement for radiopacity has limited the construction of devices to certain materials which in turn has limited the features attainable for particular applications and the available insertion techniques.

#### Summary of the Invention

In the invention, metal such as in the form of wire or filament or the like is used for constructing tubular medical endoprosthesis such as stents. Desirable attributes of these wires vary with the stent application, but include properties such as stiffness, tensile strength, elasticity, radiopacity, weldability, flexural life, conductivity, etc. These properties are hard to find in conventional wires. According to the invention, desired properties are achieved by creating a multiple metal coaxial construction. For example, it may be very desirable to have high radiopacity along with elasticity and strength. This is accomplished by combining a radiopaque metal with an elastic metal. Although it is possible to put either metal on the inside or outside, it is preferable to put the dense radiopaque material (e.g., tantalum) on the inside (core) since dense materials are generally less elastic and the elastic material (e.g., titanium or nickel-titanium alloy) on the outside (clad). The clad or "skin" of the wire will undergo more deformation in bending than the core, so the elastic component is best positioned at the skin.

- 3 -

Thus, an aspect of the invention is a metal stent device with at least a portion to be used within the body having properties that can be tailored to a particular application. The portion within the body is formed of preferably two or more dissimilar metals joined together to form a unitary member. Typically, each metal contributes a desirable property to the device which is not substantially impaired by the presence of the other metal. In particularly preferred devices, one metal provides enhanced radiopacity. In these embodiments, the stent is comprised of a metal outer member having a predetermined density and an exposed outer surface and a core including a metal having a density greater than the outer member to enhance radiopacity. The core is secured within and substantially enclosed by the outer member. Preferably, the stent is configured such that the mechanical properties, for example, the elastic properties, of the metal forming the outer member are affected by the core to a desired degree so that the stent has a desired overall performance suitable for its intended use. Preferably, the mechanical properties of the outer member dominate the properties of the stent yet the radiopacity of the member is substantially enhanced by the denser core. The invention also allows increased radiopacity of the stent without adversely affecting and in some cases improving other important properties such as the biocompatibility, small size or other performance characteristics. These performance advantages can be realized by proper selection of the material of the outer member and core, their relative size, and geometrical configuration. The particular performance characteristics to be achieved are dictated by the stent application.

The term "metal" as used herein includes electropositive chemical elements characterized by

- 4 -

ductility, malleability, luster, and conductivity of heat and electricity, which can replace the hydrogen of an acid and forms bases with the hydroxyl radical and including mixtures including these elements and alloys.

5 Many examples are given below.

An aspect of the invention features a tubular prosthesis device for use within the body. Forming the tubular endoprosthesis is a metal filament material comprised of a metal outer member of extended length  
10 having an exposed outer surface and a core within the extended outer member formed of a different metal than the outer member. The core is secured within and substantially enclosed by the outer member. The device is capable of reduction to a small size for introduction  
15 into the body lumen and expandable to a sufficiently large size to engage the wall of the body lumen.

In some preferred embodiments, the outer member and core are such that the endoprosthesis is elastic and capable of radial reduction in size without plastic  
20 deformation to the small size for introduction to the body and self-expandable by an internal elastic self-restoring force to the large size for engaging the wall of the lumen.

In other embodiments, the outer member and core  
25 are such that the endoprosthesis is plastically deformable; it is formed of small size for introduction into the body and expandable by plastic deformation to the large size for engaging the wall of the lumen.

Various embodiments of the invention may also  
30 include one or more of the following features. The device is formed into the tubular shape by knitting of the wire or filament into loosely interlocked loops of the filament. The metal of the core has a density greater than the metal of the outer member of the device. The  
35 cross sectional dimension of the filament is about 0.015

- 5 -

inch or less. The cross-sectional dimension of the filament is about 0.006 to about 0.0045 inch and the core has a cross-sectional dimension of about 0.0014 to about 0.00195 inch. The core has a density of about 9.9 g/cc or greater. The core is selected from the group consisting of tungsten, tantalum, rhenium, iridium, silver, gold, bismuth and platinum. The outer member is selected from superelastic alloys and precursors of superelastic alloys and stainless steel. The outer member is nitinol. The core is tantalum.

Another, particular aspect of the invention features a self-expanding tubular prosthesis device for use within the body formed of loosely interlocked knitted loops of a metal filament material. The filament is formed of an elastic metal capable of deflection without plastic deformation to produce a self-restoring force. The filament material is formed of an elastic metal outer member of extended length having high elasticity and an exposed outer surface, and a core of a different metal than the outer member, which core is secured within and substantially enclosed by the outer member. The device is capable of reduction to a small size for introduction into the body lumen and expandable by the internal restoring force to a sufficiently large size to engage the wall of the body lumen.

Various embodiments of this aspect as well as other aspects may include the features already mentioned as well as one or more of the following features. The core is about 25% or more of the cross-sectional dimension. The core is between about 1 and 40%, e.g. about 28% or less, preferably 33% of the cross-sectional dimension. The core has a modulus of elasticity of about 500 GPa or less, such as about 200 GPa or less.

In another aspect the invention features a medical stent device capable of placement or manipulation in the

- 6 -

body by means external of the body under guidance of a fluoroscope. The device is at least in part an elongated filament-form metal member adapted to be subjected to elastic deformation to enable the device to be forced  
5 into a characteristic deformed configuration during a stage of use and to elastically self-recover from the deformation when deformation forces are relieved. The filament-form metal member includes a core of a first metal of a first selected thickness and an intimately  
10 surrounding sheath of a second selected metal of a second thickness. The first metal is a high density metal that demonstrates characteristic relatively high radiopacity and the second metal is a lower density metal having substantially more elasticity than the first metal. The  
15 combined effect of the selected thicknesses of the first and second metals in the filament-form member serves to enhance the radio-opacity of the filament-form member to provide improved fluoroscopic or x-ray visualization of the filament-form member in the body while imparting  
20 sufficient elasticity to enable the filament-form member to elastically self-recover from its characteristic deformed configuration.

In another aspect, the invention features a tubular endoprosthesis formed of a metal member. The  
25 metal member has a cross-sectional thickness of about 0.015 inch or less, more preferably 0.0075 inch or less, and is composed of at least two different metals, including an exposed outer metal having selected mechanical properties and an inner metal encompassed  
30 within the outer metal, the inner metal having a relatively high density compared to the outer metal for enhancing the radiopacity of the endoprosthesis.

In various embodiments of any of the aspects of the invention the filament is formed by draw-forming  
35 techniques employing a large starting member which has a



- 7 -

core of metal of different properties than a surrounding metal shell.

The invention also includes methods for the use and construction of the endoprotheses described.

5 Still other aspects of the invention will be understood from the following description and from the claims.

Description of the Preferred Embodiment(s)

We first briefly describe the drawings.

10 Drawings

Fig. 1 is a perspective view of a stent according to the invention, while Fig. 1a is an enlarged view of adjacent loops of a filament knitted to form the stent;

Fig. 2 is a highly enlarged schematic cross-  
15 sectional view of the stent filament in Fig. 1a across the lines 22; while Fig. 2a is a similarly enlarged longitudinal cross-sectional view of a portion of the filament;

Fig. 3 is a schematic longitudinal cross-sectional  
20 view of a stent filament according to Fig. 2 in a bent configuration;

Figs. 4 to 4b illustrate placement of a self-expanding stent according to the invention;

Figs. 5 to 5b illustrate placement of a  
25 plastically deformable stent according to the invention;

Fig. 6 is a graph of load as a function of displacement for several stent wires according to the invention.

Description

30 Referring to Figs. 1 and 1a, an endoprosthesis stent 10 according to a preferred embodiment is adapted for use in the biliary tree and formed of an elastic filament 11 knitted into a mesh cylinder 12 that extends to ends 14, 14' coaxially along axis 13 over a working  
35 length L, about 4-6 cm and has a maximum expanded

- 8 -

diameter,  $D$ , of about 9-10 mm. The knitting forms a series of loosely interlocked knitted loops (e.g., as indicated by adjacent loops 16, 16', Fig. 1a) which may slide with respect to each other when the stent is  
5 radially compacted, for example, when delivered into the biliary duct on a catheter as further discussed below.

Referring to Figs. 2 and 2a, the filament 11 is a wire-form member that includes a longitudinal outer member 4 concentrically disposed about a central core 8  
10 which extends along an axis 6. The longitudinal member 4, having an outer diameter,  $d_o$ , about 0.0052 inch, is formed of a metal, such as nitinol, that exhibits desirable properties, such as high elasticity and biocompatibility of its exposed outer surface 7. (The  
15 surface 7 may include a non-metal coating of, e.g., fluorocarbons, silicones, hydrophilic and lubricous biocompatible materials.) The core 8 having a diameter,  $d_c$ , about 0.00175 inch, includes a metal, such as tantalum, with a density greater than the longitudinal  
20 member 4 to enhance the radiopacity of the filament and thus the stent from which it is formed. The core 8 is bonded to and substantially enclosed by the outer member 4 such that the core does not have any substantial exposed surface and therefore does not contact body  
25 tissue when positioned within the body during use. As illustrated, preferably the core 8 is a continuous solid member in intimate contact with and bonded to the interior portions of the outer member 4 without the formation of substantial voids in the interface 10  
30 between the core and outer member. Preferably, the elastic properties of the filament 11 are dominated by the elastic properties of the longitudinal member 4. The core material 8 enhances the radiopacity of the filament 11 but preferably does not substantially affect the  
35 mechanical performance of the filament. One aspect of

- 9 -

the present invention is that it has been discovered that a stent can be formed of a composite filament exhibiting substantially the elasticity properties of, for example, a solid elastic (used in linear range) or superelastic  
5 nitinol filament, (to form, for example, a self-expanding stent), despite the presence of a dense, e.g. tantalum, core, and that the stent formed of the composite filament is more radiopaque than a stent formed of a solid nitinol filament.

10 Referring to Fig. 3, the filament 11 is shown in a bent position, as it may be, for example when in use in a knitted stent device. The inner and outer portions (I) and (O), respectively, experience a wide range of compression and tension, as the filament is bent such as  
15 during knitting of the stent and during placement of the stent and in use. An advantage of the filament is that by positioning the radiopaque core material 8 near the axis 6, the range of tension and compression imposed on the core is relatively small and a wide latitude of  
20 stiff, dense, strong, and/or substantially radiopaque materials can be used which otherwise might not be suitable for their response to bending or other properties.

#### Parameter Selection

25 Generally, the characteristics of the filament and thus the selection of the outer member and core metals, is based on the stent application. Particularly preferred uses of stents of the invention are for the biliary tree (e.g. 8-12 mm diameter, 2-8 cm length) such  
30 as the hepatic and pancreatic duct (e.g. 4-12 mm diameter), the urinary tract including the prostate and urethra (e.g. 14-15 mm, diameter; 3-4 cm, length) and the ureter (e.g. 3-4 mm diameter), and the vasculature including the hepatic vasculature e.g. for the treatment  
35 of portal hypertension (e.g. 4-10 mm diameter; 5-6 cm,

- 10 -

length), the neurovasculature (e.g. 1 mm, diameter) and the aorta (e.g. 20 mm, diameter) for example, for treatment of aneurysms or lesions. A filament with a larger outer diameter,  $d_o$ , may be used for larger stents. 5 For example, a filament outer diameter,  $d_o$ , in the range of 0.008 inch may be used in the case of an aortic stent.

Typically, the dimension of the core ( $d_c$ ) is less than about 50% (but typically greater than about 1%) of the outer diameter of the filament, more preferably 10 between about 40% and 25%, for example about 33%. Embodiments of the stent having enhanced radiopacity are especially useful in applications where the stent must be sized small with, for example, a stent wire outer diameter ( $d_o$ ) of less than about 0.015 inch, e.g., even 15 less than 0.0075 inch and for which less dense metals are required for advantageous elastic properties. For example, in another embodiment the filament is formed of nitinol with an outer diameter,  $d_o$ , of about 0.006 inch and a core of tantalum with diameter,  $d_c$ , at about 0.002 20 inch.

Referring to Figs. 4 to 4b, in embodiments such as that discussed with respect to Figs. 1 and 1a, stent 10 is a self-expanding stent that may be introduced to a body lumen 20 such as the biliary tree. The stent 10 is 25 positioned on a catheter 24 which includes a sleeve 26 to maintain the stent 10 in a relatively compact form (Fig. 4). This is typically achieved by rolling the stent upon itself and a pair of tiny mandrels that nip a portion of the wall of the stent and are rotated bodily together 30 until the full circumference of the stent is taken up in the resulting rolled up form. In other cases, the stent may be positioned coaxially over the catheter. The catheter is positioned within the lumen at the region corresponding to a tumor 22 and the sleeve 26 is removed 35 from about the stent 10, for example, by withdrawing

- 11 -

axially in the direction of arrow 28, thus causing the stent 10 to radially expand by release of its internal restoring force (Fig. 4a). The internal restoring force is sufficient to dilate the lumen 20 by pushing the tumor growth 22 radially outward (or in some cases compressing the occlusion against the lumen wall), thus opening a passage that allows unobstructed flow through the lumen and allowing removal of the catheter 24 (Fig. 4b). In another embodiment, the stent may be compressed in a tube having a distal axial opening and be pushed from the end of the tube, whereby it self-expands.

Referring now to Figs. 5 to 5b, the stent may also be a plastically deformable tube-like knitted structure 50. The individual filament meshes interlock loosely in a looped pattern and during radial expansion of the knitted structure loops forming the individual meshes are deformed beyond the elastic limits of the filament, resulting in plastic deformation of the filament. Stent 50 is placed over a balloon 51 carried near the distal end of a catheter 52. The catheter 52 is directed through a lumen 54, e.g., a blood vessel until the portion carrying the balloon and stent reaches the region of the occlusion 53 (Fig. 5). The stent 50 is then radially expanded beyond its elastic limit by the admission of pressure to the balloon 51 and compressed against the vessel wall with the result that occlusion 53 is compressed, and the vessel wall surrounding it undergoes a radial expansion (Fig. 5a). The pressure is then released from the balloon and the catheter is withdrawn from the vessel (Fig. 5b).

The stent in the balloon expandable embodiment is preferably formed with a dense radiopaque core formed of tantalum and an outer member formed of plastically deformable stainless steel. While the stent filament is plastically deformable, the filament may be selected to

- 12 -

have elasticity sufficient to meet the needs of the particular vessel. In addition, self-expanding stents, such as discussed above with respect to Figs. 4 et seq. can be used with a balloon delivery system to aid  
5 dilatation of a body lumen.

In various embodiments, the metals used in the filament and their configuration are selected to exhibit various desirable characteristics. For example, the relative dimension of the core and outer member and the  
10 particular materials used for these elements may be selected based on the desired over-all mechanical properties of the stent and the degree to which x-ray visibility is to be enhanced, since the core affects the mechanical properties of the filament compared to a solid  
15 filament formed of the outer material, and the radiopacity is a function of the sum of the mass between an x-ray beam source and detector. A knitted stent with overlapping portions, may require less radiopaque material to provide sufficient visibility. Similarly,  
20 the location of use in the body may affect the amount of dense material needed for sufficient visibility. The visibility of a device can be tested by known techniques such as ASTM Designation F640-79 "Standard Test Method for Radiopacity of Plastics for Medical Use". In this  
25 test, the background densities which may be encountered clinically are mimicked by an aluminum plate positioned over the stent having various thicknesses.

The properties of the outer member metal and core which may be considered include density, modulus of  
30 elasticity (in annealed and hardened states), biocompatibility (primarily a factor for the material of the outer longitudinal member), flexural stiffness, durability, tensile and compression strength, and the required radiopacity and resolution. In some cases, if  
35 desirable, the inner and outer metals may be the same

- 13 -

metal or metals of the same elemental composition that are different metals because of e.g., different crystal structure or other properties.

In other embodiments of elastic filament members, the outer member is formed of a continuous solid mass of a highly elastic biocompatible metal such as a superelastic or pseudo-elastic metal alloy, for example, a nitinol (e.g., 55% nickel, 45% titanium). Other examples of superelastic materials include, e.g., Silver-Cadmium (Ag-Cd), Gold-Cadmium (Au-Cd), Gold-Copper-Zinc (Au-Cu-Zn), Copper-Aluminum-Nickel (Cu-Al-Ni), Copper-Gold-Zinc (Cu-Au-Zn), Copper-Zinc (Cu-Zn), Copper-Zinc-aluminum (Cu-Zn-Al), Copper-Zinc-Tin (Cu-Zn-Sn), Copper-Zinc-Xenon (Cu-Zn-Xe), Iron Beryllium (Fe<sub>3</sub>Be), Iron Platinum (Fe<sub>3</sub>Pt), Indium-Thallium (In-Tl), iron-manganese (Fe-Mn) Nickel-Titanium-Vanadium (Ni-Ti-V), Iron-Nickel-Titanium-Cobalt (Fe-Ni-Ti-Co) and Copper-Tin (Cu-Sn). See Schetsky, L. McDonald, "Shape Memory Alloys", Encyclopedia of Chemical Technology (3rd ed.), John Wiley & Sons, 1982, vol. 20. pp. 726-736 for a full discussion of superelastic alloys. Preferably in some cases of elastic filament members, nitinol or other highly elastic metal is employed as the outer member, in an arrangement in which it is never stressed beyond the straight line portion of its stress strain curve. Other examples of metals suitable for the outer member include stainless steel or the precursor of superelastic alloys. Precursors of superelastic alloys are those alloys which have the same chemical constituents as superelastic alloys, but have not been processed to impart the superelastic property under the conditions of use. Such alloys are further described in co-owned and co-pending U.S. Serial No. 07/507,375, filed April 10, 1990, by R. Sahatjian (see also PCT application US91/02420) the entire contents of which is hereby incorporated by reference.

- 14 -

The core material is preferably a continuous solid mass, but may also be in a powder-form. Typically, the core includes a metal that is relatively dense to enhance radiopacity. Preferably, the core metal has a density of about 9.9 g/cc or greater. Most preferably, the core is formed of tantalum (density = 16.6 g/cc). Other preferred materials and their density include tungsten (19.3 g/cc), rhenium (21.2 g/cc), bismuth (9.9 g/cc), silver (16.49 g/cc), gold (19.3 g/cc), platinum (21.45 g/cc), and iridium (22.4 g/cc). Typically, the core is somewhat stiffer than the outer member. Preferably, the core metal has a low modulus of elasticity, e.g., preferably below about 550 GPa, e.g., such as tantalum (186 GPa). Generally, a smaller difference between the modulus of elasticity between the outer material and core results in a smaller variation of the modulus from that of the outer material in the filament of the invention. For larger differences, a smaller core may be used so as to produce a filament in which the elastic properties are dominated by the outer material.

The outer member and core may be in many cross-sectional geometric configurations, such as circular, square, triangular, hexagonal, octagonal, trapezoidal and the geometrical configuration of the core may differ from that of the longitudinal member. For example, the outer member of a filament may be rectangular in cross-section with a rectangular core or triangular or hexagonal in cross-section with a circular core. A stent filament may also take on the form of tubing with a lumen within the core extending along the axis. A stent filament may also include successive layers of less dense outer material and more dense core material to form a multi-composite system of three layers or more from exterior to center. The core may extend intermittently along the axis in a desired pattern.



- 15 -

The filament may be a draw-form member formed, for example, by drilling out the center of a relatively large rod of the outer member material to form a bore, positioning a rod of core material in the bore, sealing the ends of the bore, e.g., by crimping, and drawing the form through a series of dies of decreasing diameter until the desired outer diameter is achieved. The component may be heat treated to anneal, harden or impart superelastic properties. Other methods of formation are also possible, e.g., by coating the core with the desired outer material such as by electro- or electroless plating. The materials used in the outer member and core are also selected based on their workability for forming the filament, including factors such as machinability, for forming the longitudinal member into a tubular piece and the core member into a rod shaped piece, stability in gaseous environments at annealing temperatures, properties related to drawing, welding, forging, swaging, the ability to accept coatings such as adhesives, polymers, lubricants and practical aspects such as cost and availability.

As evident from the above, the stents of the invention are preferably constructed by knitting a filament, most preferably on a circular knitting machine. Knitted metal stents are discussed, for example, in Strecker, U.S. 4,922,905. It will be appreciated that the stent may be formed from a composite metal filament by other means such as weaving, crocheting, or forming the filament into a spiral-spring form element. It will further be appreciated that the composite filament may be incorporated within a stent formed from conventional metal or non-metal materials (e.g. dacron in the case of an aortic graft) to contribute desirable properties such as strength and/or radiopacity. The stent may also be in the form of a metal member configured as other than a

- 16 -

filament-form, e.g., a composite sheet form member in the form of a cuff or tube.

The following example is illustrative of a stent filament.

Example

5           An elastic, radiopaque filament for use in a stent may be formed as follows. A 500 foot length of filament (0.0052 inch in diameter) having an outer member formed of a precursor of a nitinol (55% Ni/45% Ti) superelastic  
10 alloy and a core material of tantalum (0.00175 inch in diameter) is formed by drilling a 0.25 inch diameter bore in a 0.75 inch rod of the outer member material and providing in the drilled lumen a tantalum member of substantially matched outer diameter. The rod is  
15 mechanically forged in a standard hot forging and rolling apparatus, then hammered such that no substantial voids between the core and outer longitudinal member are present. One end of the rod is sealed and the opposite end is cold drawn longitudinally through a die to the  
20 final diameter. Initially, the outer member of the filament is the precursor of a superelastic alloy, i.e., it has not been heat treated to impart the superelastic property under the anticipated conditions of use.

Referring to Fig. 6, load versus displacement  
25 curves are illustrated. (For clarity, curves C, D and A are offset, successively, 0.025 inch on the x-axis.) Curve A illustrates the filament as discussed in the above paragraph prior to heat annealing which induces the superelastic property; the filament exhibits  
30 substantially linear elastic strain as a function of stress to a break point z. Curves B, C, D illustrate stress/strain curves after annealing the filament at 460°C for 3 minutes, 5 minutes and 15 minutes, respectively. As these curves illustrate, the  
35 superelastic nature of the filament is substantially

preserved, as evidenced by the substantial plateaus (p) on the stress/strain curve, despite the presence of the tantalum core. Also as illustrated, the stress at which constant displacement occurs decreases with increasing  
 5 annealing, as would be expected with a superelastic material. The mechanical properties of the filament, therefore, are dominated by the nitinol alloy, despite the presence of the tantalum core.

Referring to Table I, the modulus of elasticity  
 10 and plateau stress calculated based on stress-strain measurements as above, are compared for the filaments of the invention and a solid filament of Ni-Ti alloy.

Table I			
	Ni-Ti	Ta Cored Ni-Ti	% Change in Cored
15			
<u>Filament</u>			
Diameter	.0038"	.0052"	--
Area	$1.134 \times 10^{-5} \text{ in}^2$	$2.124 \times 10^{-5} \text{ in}^2$	--
(Modulus of Elasticity)			
20 Precursor	5,401,300 psi	7,373,865 psi	+27%
460° @ 3 mins	6,967,150 psi	6,657,000 psi	-4.5%
460° @ 5 mins	5,381,160 psi	5,721,100 psi	+6.0%
460° @ 10 mins	5,139,310 psi	-----	--
460° @ 15 mins	5,143,960 psi	5,551,924	+7.4%
25 Plateau Stress			
(loading)			
460° @ 3 mins	101,400 psi	94,174	-7.2%
460° @ 5 mins	89,056 psi	84,757	-4.8%
460° @ 10 mins	79,357 psi	-----	--
30 460° @ 15 mins	72,303 psi	75,339 psi	+4.1%

As the results in Table I illustrate, the modulus of elasticity of the filaments of the invention was varied less than 30% compared to the solid Ni-Ti  
 35 filament. The plateau stress of the filaments of the invention using a superelastic outer member was varied less than about 10% compared to a solid Ni-Ti superelastic filament. The composite filament formed as described exhibits about 30% or more enhanced x-ray  
 40 visibility over a filament of the same thickness formed of solid nitinol.

- 18 -

It will be understood that such filaments may be employed both in instances where the superelastic property is employed, and in instances where it is not (all stress within the straight line portion of the stress strain curve).

The visibility of a knitted stent formed from the filament was greater than a comparison stent using a solid nitinol filament of larger (0.006 inch) diameter, yet using the stent of the invention, the force needed for radial compression of the stent was reduced compared to the stent formed of the thicker nitinol filament. Thus, radiopacity of the stent was enhanced while mechanical properties were dominated by the outer member, nitinol. Placement of the stent, as described above, can be monitored by x-ray fluoroscopy.

Preferably, filaments as described, dominated by the mechanical properties of an outer member, such as nitinol, and exhibiting generally satisfactory radiopacity have outer diameter ( $d_o$ ) of about 0.008 to 0.0045 inch with a core, for example of tantalum, with diameter ( $d_c$ ) of about 0.0014 to 0.00195 inch.

Other embodiments are in the following claims.

- 19 -

Claims

1. A tubular prosthesis device for use within the body comprised of a metal filament material formed of a metal outer member of extended length having an exposed  
5 outer surface, and

a core within said extended outer member comprising a different metal than said outer member, said core being secured within and substantially enclosed by said outer member,

10 said device being capable of reduction to a small size for introduction into said body lumen and expandable to a sufficiently large size to engage the wall of said body lumen.

2. The device of claim 1 wherein said outer  
15 member and core are constructed such that said endoprosthesis is elastic and capable of radial reduction in size without plastic deformation to said small size for introduction to the body and self-expandable by an internal elastic self-restoring force to said large size  
20 for engaging said wall of said lumen.

3. The device of claim 1 wherein said outer member and core are such that the endoprosthesis is plastically deformable and formed into said small size for introduction into the body and expandable by plastic  
25 deformation to said large size for engaging the wall of said lumen.

4. The device of claim 2 or 3 wherein said device is formed into said tubular shape by knitting into loosely interlocked loops of said filament.

- 20 -

5. The device of any one of claims 1, 2 or 3 wherein said metal of said core has a density greater than said metal of said outer member of said device.

6. The device of claim 5 wherein said cross sectional dimension of said filament is about 0.015 inch or less.

7. The device of claim 6 wherein said cross-sectional dimension of said filament is about 0.006 to about 0.0045 inch and said core has across-sectional dimension of about 0.0014 to about 0.00195 inch.

8. The device of claim 7 wherein said core has a density of about 9.9 g/cc or greater.

9. The device of claim 8 wherein said core is selected from the group consisting of tungsten, tantalum, rhenium, iridium, silver, gold, bismuth and platinum.

10. The device of claim 9 wherein said outer member is selected from superelastic alloys and precursors of superelastic alloys and stainless steel.

11. The device of claim 10 wherein said outer member is nitinol.

12. The device of claim 11 wherein said core is tantalum.

13. A self-expanding tubular prosthesis device for use within the body comprised of loosely interlocked knitted loops of a metal filament material formed of an elastic material capable of deflection without plastic deformation to produce a self-restoring force, said

- 21 -

filament material comprising an elastic metal outer member of extended length and an exposed outer surface, and

a core comprising a different metal than said outer member, said core being secured within and substantially enclosed by said outer member,

said device being capable of reduction to a small size for introduction into said body lumen and expandable by said internal restoring force to a sufficiently large size to engage the wall of said body lumen.

14. The device of claim 13 wherein said core is about 1 to 40% of said of the cross-sectional dimension of said filament.

15. The device of claim 14 wherein said core is about 25% or more of said cross-sectional dimension.

16. The device of claim 15 wherein said core is about 33% of said cross-sectional dimension.

17. The device of claim 14 wherein said core has a modulus of elasticity of about 500 GPa or less.

18. The device of claim 15 wherein said core has a modulus of elasticity of about 200 GPa or less.

19. The device of claim 14 wherein said core has a density of about 9.9 g/cc or greater.

20. The device of claim 19 wherein said core is selected from the group consisting of tungsten, tantalum, rhenium, iridium, silver, gold, bismuth and platinum.

- 22 -

21. The device of claim 20 wherein said outer member is selected from the group consisting of superelastic alloys and precursors of superelastic alloys and stainless steel.

5        22. The device of claim 21 wherein said outer member is nitinol.

23. The device of claim 22 wherein said core is tantalum.

24. The device of claim 13 or 23 wherein said  
10 cross sectional dimension of said filament is about 0.015 inch or less.

25. A medical stent device capable of placement or manipulation in the body by means external of the body under guidance of a fluoroscope, said device comprised at  
15 least in part of an elongated filament-form metal member adapted to be subjected to elastic deformation to enable the device to be forced into a characteristic deformed configuration during a stage of use and to elastically self-recover from said deformation when deformation  
20 forces are relieved, said filament-form metal member comprised of a core of a first metal of a first selected thickness and an intimately surrounding sheath of a second selected metal of a second thickness, said first metal being a high density metal that demonstrates  
25 characteristic relatively high radiopacity and said second metal being a lower density metal having substantially more elasticity than said first metal, the combined effect of the selected thicknesses of said first and second metals in said filament-form member serving to  
30 enhance the radio-opacity of said filament-form member to provide improved fluoroscopic or x-ray visualization of



- 23 -

said filament-form member in the body while imparting sufficient elasticity to enable the filament-form member to elastically self-recover from its characteristic deformed configuration.

5           26. The medical device of claim 25 wherein said filament-form metal member comprises a draw-form.

27. The medical device of claim 26 wherein said second metal is nitinol.

28. The medical device of claim 27 wherein said  
10 high density metal is tantalum.

29. A tubular endoprosthesis device for use within the body comprised of a metal member formed in tubular shape, wherein said metal member has a cross-sectional thickness of about 0.015 inch or less and is  
15 composed of at least two different metals, including an exposed outer metal having select mechanical properties and an inner metal encompassed within said outer metal, said inner metal having a relatively high density compared to said outer metal for enhancing the  
20 radiopacity of said endoprosthesis.

30. The tubular prosthesis device of claim 29 wherein said metal member has a cross-sectional thickness of about 0.0075 inch or less.

## AMENDED CLAIMS

[received by the International Bureau on 25 August 1993 (25.08.93);  
original claims 1-4,6,7,13-16,24-26,29 and 30 amended;  
new claims 31-33 added; other claims unchanged (6 pages)]

1. A tubular prosthesis device for placement  
within a lumen of the body comprised of at least one  
filament-form metal element formed of a metal outer  
5 member of extended length, and  
a core within said extended outer member  
comprising a different metal than said outer member, said  
core being secured within and substantially enclosed by  
said outer member,  
10 said filament-form metal element being multiply  
bent and configured to form at least part of said tubular  
prosthesis device,  
said tubular prosthesis device being of small  
size for introduction into said body lumen and expandable  
15 to a sufficiently large size to engage the wall of said  
body lumen.

2. The device of claim 1 wherein said outer  
member and core are constructed such that said prosthesis  
is elastic and capable of radial reduction in size  
20 without plastic deformation to said small size for  
introduction to the body and being self-expandable by  
internal elastic self-restoring force to said large size  
for engaging said wall of said lumen.

3. The device of claim 1 wherein said outer  
25 member and core are such that the prosthesis is  
plastically deformable, said device being originally  
formed in said small size for introduction into the body  
and being expandable by plastic deformation to said large  
size for engaging the wall of said lumen.

30 4. The device of claim 2 or 3 wherein said device  
is formed into said tubular shape by knitting into

- 25 -

loosely interlocked loops of said filament-form metal element.

5. The device of any one of claims 1, 2 or 3 wherein said metal of said core has a density greater than said metal of said outer member of said device.

6. The device of claim 5 wherein the transverse cross-sectional dimension of said filament-form metal element is about 0.015 inch or less.

7. The device of claim 6 wherein said transverse cross-sectional dimension of said filament-form metal element is about 0.0045 to about 0.006 inch and said core has a transverse cross-sectional dimension of about 0.0014 to about 0.00195 inch.

8. The device of claim 7 wherein said core has a density of about 9.9 g/cc or greater.

9. The device of claim 8 wherein said core is selected from the group consisting of tungsten, tantalum, rhenium, iridium, silver, gold, bismuth and platinum.

10. The device of claim 9 wherein said outer member is selected from superelastic alloys and precursors of superelastic alloys and stainless steel.

11. The device of claim 10 wherein said outer member is nitinol.

12. The device of claim 11 wherein said core is tantalum.

- 26 -

13. A self-expanding tubular prosthesis device for placement within a lumen of the body comprised of loosely interlocked knitted loops of at least one filament-form metal element formed of an elastic material  
5 capable of deflection without plastic deformation to produce a self-restoring force,

said filament-form metal element comprising an elastic metal outer member of extended length, and  
a core comprising a different metal than said  
10 outer member, said core being secured within and substantially enclosed by said outer member,

said device being capable of reduction to a small size for introduction into said body lumen and expandable by said self-restoring force to a sufficiently large size  
15 to engage the wall of said body lumen.

14. The device of claim 13 wherein the transverse cross-sectional dimension of said core is about 1 to 40% of the transverse cross-sectional dimension of said filament-form metal element.

20 15. The device of claim 14 wherein said core is about 25% or more of said transverse cross-sectional dimension.

16. The device of claim 15 wherein said core is about 33% of said transverse cross-sectional dimension.

25 17. The device of claim 14 wherein said core has a modulus of elasticity of about 500 GPa or less.

18. The device of claim 15 wherein said core has a modulus of elasticity of about 200 GPa or less.

- 27 -

19. The device of claim 14 wherein said core has a density of about 9.9 g/cc or greater.

20. The device of claim 19 wherein said core is selected from the group consisting of tungsten, tantalum, rhenium, iridium, silver, gold, bismuth and platinum.

21. The device of claim 20 wherein said outer member is selected from the group consisting of superelastic alloys and precursors of superelastic alloys and stainless steel.

22. The device of claim 21 wherein said outer member is nitinol.

23. The device of claim 22 wherein said core is tantalum.

24. The device of claim 13 or 23 wherein the transverse cross-sectional dimension of said filament-form metal element is about 0.015 inch or less.

25. A tubular medical stent device capable of placement or manipulation in the body by means external of the body under guidance of a fluoroscope, said device comprised at least in part of an elongated filament-form metal element adapted to be subjected to elastic deformation to enable the device to be forced into a characteristic deformed configuration during a stage of use and to elastically self-recover from said deformation when deformation forces are relieved, said filament-form metal element comprised of a core of a first metal of a first selected thickness and an intimately surrounding sheath of a second selected metal of a second thickness, said first metal being of a substantially higher density

- 28 -

and demonstrating characteristically substantially higher radiopacity than that of said second metal, said second metal being substantially more elastic than said first metal, the combined effect of the selected thicknesses of  
5 said first and second metals in said filament-form metal element serving to enhance the radiopacity of said filament-form metal element to provide improved fluoroscopic or x-ray visualization of said filament-form metal element in the body while imparting sufficient  
10 elasticity to enable the filament-form metal element to elastically self-recover from its characteristic deformed configuration.

26. The medical device of claim 25 wherein said filament-form metal element is the product produced by  
15 draw-forming.

27. The medical device of claim 26 wherein said second metal is nitinol.

28. The medical device of claim 27 wherein said high density metal is tantalum.

20 29. A hollow tubular prosthesis device for use within the body comprised of a filament-form metal element configured to form a hollow tubular shape, wherein said filament-form metal element has a transverse cross-sectional dimension of about 0.015 inch or less and  
25 is composed of at least two different metals, including an outer metal having selected mechanical properties and an inner metal encompassed within said outer metal, said inner metal having a substantially higher density than said outer metal for enhancing the radiopacity of said  
30 hollow tubular prosthesis.

- 29 -

30. The hollow tubular prosthesis device of claim 29 wherein said filament-form metal element has a transverse cross-sectional dimension of about 0.0075 inch or less.

5           31. A medical device for use in the body comprised of at least one filament-form metal element formed of a metal outer member of extended length and a core of extended length within said extended outer member comprising a different metal than said outer member, said  
10 core metal having greater radiopacity than said outer member, said core metal selected from the group consisting of tungsten, tantalum, rhenium, iridium, silver, gold, bismuth and platinum.

32. The medical device of claim 31 wherein said  
15 filament-form metal element is the product produced by draw-forming.

33. The medical device of claim 31 where said metal of said outer member is substantially more elastic than the metal of said core.

1/5




FIG. 1




FIG. 1a






FIG. 2




FIG. 2a




FIG. 3

3/5




FIG. 4




FIG. 4a




FIG. 4b




FIG. 5




FIG. 5a




FIG. 5b




FIG. 6

## INTERNATIONAL SEARCH REPORT

PCT/US93/02970

<b>A. CLASSIFICATION OF SUBJECT MATTER</b>														
IPC(5) :A61M 29/02; A61F 2/04 US CL :623/1, 12; 606/194, 195 According to International Patent Classification (IPC) or to both national classification and IPC														
<b>B. FIELDS SEARCHED</b>														
Minimum documentation searched (classification system followed by classification symbols) U.S. : 428/386, 389, 397, 364, 375, 378, 379; 623/12														
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched														
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)														
<b>C. DOCUMENTS CONSIDERED TO BE RELEVANT</b>														
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.												
<u>Y</u> A	US, A, 4,950,227 (Savin et al.) 21 August 1990, See column 5, lines 40-54; column 4, lines 9-16; and figures 1 and 2.	1 - 1 0 , 1 3 - 21,24/13,25,26,2 9,30  11,12,22,23,24/2 3,27,28												
<u>Y</u> A	US, A, 5,069,226 (Yamauchi et al.) 03 December 1991, See column 8, lines 1-54; column 2, lines 50-56; column 5, line 17-column 6, line 36.	1 - 1 0 , 1 3 - 21,24/13,25,26,2 9,30  11,12,22,23,24/2 3,27,28												
<input type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.														
<table border="0"> <tr> <td>* Special categories of cited documents:</td> <td>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</td> </tr> <tr> <td>"A" document defining the general state of the art which is not considered to be part of particular relevance</td> <td>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</td> </tr> <tr> <td>"E" earlier document published on or after the international filing date</td> <td>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</td> </tr> <tr> <td>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</td> <td>"G" document member of the same patent family</td> </tr> <tr> <td>"O" document referring to an oral disclosure, use, exhibition or other means</td> <td></td> </tr> <tr> <td>"P" document published prior to the international filing date but later than the priority date claimed</td> <td></td> </tr> </table>			* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention	"A" document defining the general state of the art which is not considered to be part of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone	"E" earlier document published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art	"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"G" document member of the same patent family	"O" document referring to an oral disclosure, use, exhibition or other means		"P" document published prior to the international filing date but later than the priority date claimed	
* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention													
"A" document defining the general state of the art which is not considered to be part of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone													
"E" earlier document published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art													
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"G" document member of the same patent family													
"O" document referring to an oral disclosure, use, exhibition or other means														
"P" document published prior to the international filing date but later than the priority date claimed														
Date of the actual completion of the international search 07 JUNE 1993		Date of mailing of the international search report 01 JUL 1993												
Name and mailing address of the ISA/US Commissioner of Patents and Trademarks Box PCT Washington, D.C. 20231		Authorized officer DEBRA S. BRITTINGHAM												
Facsimile No. NOT APPLICABLE		Telephone No. (703) 308-3401												

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER: \_\_\_\_\_**

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**